

Technical Data Sheet
Edge Protectors

Physical Properties	Test Values	Standards
Hardness 5 Sec	57 SH A	ISO 868
Density	1.09	ISO 2781
Tensile Strength at Break	7.8 Mpa	ISO 37
Elongation at Break	700%	ISO 37
D.R.C 24H At 23°C	20%	ISO 815 type B
DRC 24H AT 70°C	46%	ISO 815 type B
Temperature Resistance	-35°C to +75 °c	
Colour	Colourable Beige	

Polymax's TPE P404 is a thermoplastic elastomer rubber of TPS-SBS/S.E.B.S type. This quality offers a good resistance to atmospheric agents, ageing, to UV and to usual chemical products (excluding organic solvents, aromatic and vegetable oils)

Polymax's TPE P404 is 100% recyclable. EU 2002/95/EC RoHS & 200/53CE Reduction of Grey Energy (energy cost of production and transport):

- Lower energy cost of production: no firing after extrusion
- Low density: lower carbon footprint & cheaper freight costs

This quantity is compatible with silicone sealants: DOW Dow Corning 719 & Dow Corning Fire Stop 700, SIKASIKASIL SG 500 & WS 605S, ILLBRUCK Perenator FS 121.

It is also compatible with self-cleaning glasses: Bioclean from SAINT GOBAIN & Pilkington Active from PILKINGTON.

Food Contact According Suppliers Datas

Not suitable for food applications

Compliance with Rules

Regulation CE N° 1907/2006 REACH

Directive 2002/95/EC (RoHS): We are not aware of any lead, mercury, hexavalent chromium, polybrominated biphenyls (PBB) or polybrominated diphenylethers (PBDE) being present in our compounds beyond permissible levels.

Directive 2002/96/EC (WEEE): We are not aware of any polychlorinated biphenyls (PCB), polychlorinated terphenyls (PCB/PCT), mercury, brominated flame-retardants, asbestos, chlorofluorocarbons (CFC), hydrochlorocarbons (HCFC), hydrofluorocarbons (HFC), ceramic fibres or radioactive substances being present in our compounds beyond permissible levels.