

Building 91D, Prince Philip Barracks, SEME, Budds Lane, Bordon, Hampshire, GU35 0FJ, UK Tel: +44 (0) 1420 474 123 Fax: +44 (0) 1420 487 816 E-mail: sales@polymax.co.uk Web: www.polymax.co.uk

Polymax Vega

In food and beverage plants and equipment's where contact with milk, vegetable and animal oil is encountered and necessity to maintain a clean environment

Colour	Off White
Compound	NBR
Density [specific gravity]	1.35
Hardness [Degrees Shore A]	60° ± 5°
Tensile Strength [Mpa]	6.0
Elongation at break	300
Minimum Temperature	-20°C
Maximum temperature	+110°C
Abrasion resistance [mm3]	250

FDA Approved.
Odour free and tasteless