

Technical Information — Rev. 1, July 2010

## Product Description

DuPont™ Kalrez® Spectrum™ 7090 perfluoroelastomer parts are specifically targeted for use in applications requiring high hardness/higher modulus properties. These specialty black parts have excellent mechanical properties including compression set resistance, seal force retention, response to temperature cycling effects and rapid gas decompression resistance. Kalrez® Spectrum™ 7090 perfluoroelastomer parts are well suited for both static and dynamic sealing applications, especially applications that require extrusion resistance at higher temperatures. They also offer outstanding thermal stability and chemical resistance. A maximum continuous service temperature of 325 °C (617 °F) is suggested. Short excursions to higher temperatures may also be possible.

## Typical Physical Properties<sup>1</sup>

Color	Black
Hardness, Shore A <sup>2</sup>	90
50% Modulus <sup>3</sup> , MPa (psi)	15.51 (2250)
Tensile Strength at Break <sup>3</sup> , MPa (psi)	22.75 (3300)
Elongation at Break <sup>3</sup> , %	75
Compression Set <sup>4</sup> , %	
70 hr at 204 °C	12
70 hr at 260 °C	23
Temperature of Retraction, Tr10 <sup>5</sup> , °C (°F)	-5 (23)
Maximum Continuous Service Temperature <sup>6</sup> , °C (°F)	325 (617)

<sup>1</sup> Not to be used for specification purposes

<sup>2</sup> ASTM D2240 (pellet test specimens)

<sup>3</sup> ASTM D1414 and D412 (AS568 K214 O-ring test specimens)

<sup>4</sup> ASTM D1414 and D395B (AS568 K214 O-ring test specimens)

<sup>5</sup> ASTM D1329 (dumbbell test specimens/test specimens stretched 25%)

<sup>6</sup> DuPont proprietary test method

## Performance Features/Benefits


- Higher hardness and modulus
- Exceptional thermal stability and compression set resistance
- Outstanding seal force retention properties and response to temperature cycling effects
- Excellent mechanical properties
- Lower coefficient of thermal expansion (CTE) versus other Kalrez® parts thus minimizing the need to increase the free volume of the seal gland when upgrading from fluoroelastomers (FKM) to perfluoroelastomers (FFKM)



The miracles of science™

## Long-Term Compression Set in Hot Air<sup>1</sup>

672 hour at 260 °C (500 °F)



<sup>1</sup> Not to be used for specification purposes

<sup>2</sup> ASTM D1414 and D395B (AS568 K214 O-ring test specimens)

Visit us at [kalrez.dupont.com](http://kalrez.dupont.com) or [vespel.dupont.com](http://vespel.dupont.com)

Contact DuPont at the following regional locations:

**North America**  
800-222-8377

**Latin America**  
+0800 17 17 15

**Europe, Middle East, Africa**  
+41 22 717 51 11

**Greater China**  
+86-400-8851-888

**ASEAN**  
+65-6586-3688

**Japan**  
+81-3-5521-8484

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable and falls within the normal range of properties. It is intended for use by persons having technical skill, at their own discretion and risk. This data should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents.

**Caution:** Do not use in medical applications involving permanent implantation in the human body. For other medical applications, discuss with your DuPont customer service representative and read Medical Caution Statement H-50103-3.

Copyright © 2010 DuPont. The DuPont Oval Logo, DuPont™, The miracles of science™, Kalrez®, Kalrez®Spectrum™, and Vespel® are trademarks or registered trademarks of E.I. du Pont de Nemours and Company or its affiliates. All rights reserved.

(06/07) Reference No. KZE-A10576-00-B0710



*The miracles of science™*